

No. 1523923.9R

(Please quote this number in all correspondence)

CLIENT:
Belgotex
25 Leslie Hills Drive
Riccarton, Christchurch

Attn.: Geri Hansen

SAMPLE RECEIVED FROM:
BelgotexSAMPLE DESCRIPTION:
Tufted level loop pile carpet – Auburn Ridge
Nominal Composition – 100% Wool
Nominal Yarn Weight – 1084gsm

Date Received: 12.7.24

Client Order No.: PO48289

Client Reference:

1 of 2

AS/ISO 9239.1:2003, PART 1 – REACTION TO FIRE TESTS FOR FLOORINGS. DETERMINATION OF THE BURNING BEHAVIOUR USING A RADIANT HEAT SOURCE

Note: This test was sub-contracted (Test No. 24-003008).

CHF Value	1	2	3	Mean
Length (kW/m ²)	4.4	4.2	3.9	4.2
Width (kW/m ²)	8.6	-	-	-
Smoke Value				
Length (%.min)	78	90	74	81
Width (%.min)	50	-	-	-

HF30 not reported as flame out time occurred before 30 minutes.

The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be sole criterion for assessing the potential fire hazard of the product in use.

Sample was conditioned in accordance with BSEN 13238:2010 at a temperature of 23 ±2°C and relative humidity of 50 ±5% for a minimum of 48 hours prior to testing.

Results in accordance with section 9.4 have not been included in the report. They are available upon request.

Each specimen was loose laid over Dunlop Eureka 10mm underlay and 6mm thick fibre reinforced cement board and clamped prior to testing.

Note: This report supersedes NZWTA report no. 1523923.9 dated 27/08/2024.

“THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED”

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.


C Judan
Key Technical Person

29/08/2024

No. 1523923.9R

(Please quote this number in all correspondence)

CLIENT:
Belgotex
25 Leslie Hills Drive
Riccarton, Christchurch

Attn.: Geri Hansen


SAMPLE RECEIVED FROM:
BelgotexSAMPLE DESCRIPTION:
Tufted level loop pile carpet – Auburn Ridge
Nominal Composition – 100% Wool
Nominal Yarn Weight – 1084gsm

Date Received: 12.7.24

Client Order No.: PO48289

Client Reference:

2 of 2

**"THIS REPORT APPLIES ONLY TO THE SAMPLES TESTED"**

Samples and their identifying descriptions have been provided by the client unless otherwise stated. NZWTA Ltd makes no warranty, implied or otherwise as to the source of the tested samples. The above results are designed to provide THE CLIENT WITH GUIDANCE INFORMATION ONLY. This document shall not be reproduced except in full.


C Judan
Key Technical Person

29/08/2024



This document was created with the Win2PDF "Print to PDF" printer available at

<https://www.win2pdf.com>

This version of Win2PDF 10 is for evaluation and non-commercial use only.

Visit <https://www.win2pdf.com/trial/> for a 30 day trial license.

This page will not be added after purchasing Win2PDF.

<https://www.win2pdf.com/purchase/>